

Sự tương thích giữa các loại mỡ bôi trơn



	Aluminum complex	Barium	Calcium	Calcium 12-HSA	Calcium complex	Clay (Bentone)	Lithium	Lithium 12-HAS	Lithium complex	Polyurea*	Sodium	Calcium Sulfonate	Silica
Aluminum complex	/	■	■	●	■	■	■	■	●	■	■	■	●
Barium	■	/	■	●	■	■	■	■	■	■	■	▲	●
Calcium	■	■	/	●	■	●	●	▲	●	■	■	N/A	N/A
Calcium 12-HSA	●	●	●	/	▲	●	●	●	●	■	■	N/A	N/A
Calcium complex	■	■	■	▲	/	■	■	■	●	●	■	●	■
Clay (Bentone)	■	■	●	●	■	/	■	■	■	■	■	■	●
Lithium	■	■	●	●	■	■	/	●	●	■	■	●	●
Lithium 12-HSA	■	■	▲	●	■	■	●	/	●	■	■	●	N/A
Lithium complex	●	■	●	●	●	■	●	●	/	■	■	●	●
Polyurea*	■	■	■	■	●	■	■	■	■	★	■	■	■
Sodium	■	■	■	■	■	■	■	■	■	■	/	■	■
Calcium Sulfonate	■	▲	N/A	N/A	●	■	●	●	●	■	■	/	N/A
Silica	●	●	N/A	N/A	■	●	●	N/A	●	■	■	N/A	/

- Compatible
- ▲ Border line compatible
- Incompatible

★ Not all polyurea greases are mutually compatible